

DTM Topcoat Black / White High Gloss

2K DTM Black / White

For small damage repair jobs on existing black or white surfaces. No Primer necessary. For best corrosion protection it is recommended to use 2K Epoxy Primer 3680032/33/34 or 2K Wash Primer 3684029. Ideal for use on trailers, trucks, lift-gates, service bodies, flatbeds, restoration projects and many home projects.

Advantages

- › Easy to use
- › High quality two component DTM coating
- › Direct to Metal (Steel/ Galvanized Steel/ Aluminum)
- › Highest chemical and weather resistance
- › Long lasting and very durable finish
- › Heat resistant up to 180°C/350°F short time exposure and up to 150°C/300°F long time exposure

Article Number

Black 368 0222 (347 g / 12.2 oz.)

White 368 0223 (341 g / 12.0 oz.)

Application Notes

- › Recommend 3 passes of 1.2 mil each, flash 10 minutes @ 20°C / 68°F
- › Dry time 3 hours @ 20°C / 68°F
- › Pot life after activation 24 hours @ 20°C / 68°F



DTM Topcoat Black / White High Gloss

2K DTM Black / White

For small damage repair jobs on existing black or white surfaces. No Primer necessary. For best corrosion protection it is recommended to use 2K Epoxy Primer 3680032/33/34 or 2K Wash Primer 3684029. Ideal for use on trailers, trucks, lift-gates, service bodies, flatbeds, restoration projects and many home projects.

Advantages

- › Easy to use
- › High quality two component DTM coating
- › Direct to Metal (Steel/ Galvanized Steel/ Aluminum)
- › Highest chemical and weather resistance
- › Long lasting and very durable finish
- › Heat resistant up to 180°C/350°F short time exposure and up to 150°C/300°F long time exposure

Article Number

Black 368 0222 (347 g / 12.2 oz.)

White 368 0223 (341 g / 12.0 oz.)

Application Notes

- › Recommend 3 passes of 1.2 mil each, flash 10 minutes @ 20°C / 68°F
- › Dry time 3 hours @ 20°C / 68°F
- › Pot life after activation 24 hours @ 20°C / 68°F

